

# Technical data sheet

## SIGA-Fentrim® 20



**Updated on:** 02/02/2016

**Distributor:** SIGA Cover, Inc.

**Instructions:** see manual

**Construction:** special film/fleece combination (that can be plastered over)  
made of PO with SIGA high-performance adhesive

**Packaging unit:**

Fentrim 20 100 mm	6 rolls / box
Fentrim 20 150 mm	4 rolls / box
Fentrim 20 200 mm	2 rolls / box
Fentrim 20 50/85 mm	6 rolls / box

### Characteristics:

Property		Standards	Units	Values
Dimensions	length / width	Fentrim 20 100mm	m / m feet / inch	25 / 0.1    82 / 3.9
		Fentrim 20 150mm		25 / 0.15    82 / 5.9
		Fentrim 20 200mm		25 / 0.2    82 / 7.8
		Fentrim 20 50/85mm		25 / 0.135    82 / 5.3
Thickness*			mil / mm	26 / 0.7
Temperature resistance			°C °F	-40 °C to +100 °C -40 °F to +212 °F
Processing temperature			°C °F	from -10 °C from +14 °F
Water vapor transmission		ASTM E-96A	US perm	0.17
Specification for self-adhered flashing used for exterior wall fenestration installation		AAMA 711-13		Type A (no primer)
			Level 3 thermal exposure (80 °C/176 °F for 7 days)	
Tensile strength		ASTM D5034 per AAMA 711-13		Pass
Water penetration resistance around nails	initial	modified ASTM D1970 per AAMA 711-13		Dry / Pass
	after thermal cycling			

\*average

Property		Standards	Units	Values
<b>90° Peel adhesion</b>	OSB	ASTM D3330 per AAMA 711-13		Pass
	anodized aluminum			Pass
	extruded PVC			Pass
	plywood			Pass
	accelerated aging with UV-A	conditioning per AAMA 711-13		Pass
	elevated temperature exposure			Pass
	thermal cycling			Pass
	adhesion after water immersion			Pass
<b>Cold temperature pliability</b>	cracking	conditioning per AAMA 711-13		None / Pass
	adhesion loss			None / Pass
<b>Resistance to peeling from itself</b>		conditioning per AAMA 711-13		Pass
<b>Chemical compatibility with tested sealants</b>	(see current list of tested sealants at <a href="http://www.sigacover.com">www.sigacover.com</a> )	AAMA 713-08		Pass / Level 3 thermal exposure (80 °C/176 °F for 14 days)
<b>Ageing resistance</b>	high permanent adhesive strength, non-drying and non-embrittling since without caoutchouc, resin or solvent, can reliably and durably absorb structural movements			
<b>Suitability for storage</b>	unlimited; store in a cool, dry place in its original box			
<b>Color</b>	white			