

Technical data sheet

SIGA-Majcoat® SOB / Majcoat®



Updated on: 16/01/2017

Distributor: SIGA Cover, Inc.

Type of application: breathable membrane with/without integrated dual adhesive zone, for durably rainproof and windtight building envelopes for pitched roofs and facades

Instructions: see manual

Palett: 30 rolls bound in layers

Composition: 3-layered; functional layer reinforced on both sides with PP nonwoven

Characteristics:

		Standards	Units	Values
Dimensions	length / width / straightness		m / m / - feet / feet / -	50 / 1.5 / passed 164 / 4.9 / passed
Total weight			g/m ² oz/ft ²	190 0.62
Thickness			mm mils	0.6 23
Tear strength	MD CD	ASTM D-1117	lbs	35 35
Breaking strength	MD CD	ASTM D-882	lbs/in	40 32
Water vapor transmission		ASTM E-96 Method B	US perm	34
Water resistance		AATCC-127	cm	> 500
Flame Spread Index		ASTM E-84	class	A
Temperature resistance			°F °C	-40 °F to +176 °F -40 °C to +80 °C